


PRV

PATENT- OCH REGISTRERINGSVERKET
Patentavdelningen

SE 01/23

PCT/SE 01 / 0 0 0 2 3



Intyg
Certificate

Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.

Ansökan ingavs ursprungligen på engelska.

This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.

The application was originally filed in English.


(71) Sökande AstraZeneca AB, Södertälje SE
Applicant (s)

(21) Patentansökningsnummer 0000090-1
Patent application number

(86) Ingivningsdatum 2000-01-13
Date of filing

Stockholm, 2001-02-07

För Patent- och registreringsverket
~~For the Patent- and Registration Office~~


Leena Ullén

Avgift
Fee

PRIORITY

DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

PATENT- OCH
REGISTRERINGSVERKET
SWEDEN

Postadress/Adress
Box 5055
S-102 42 STOCKHOLM

Telefon/Phone
+46 8 782 25 00
Vx 08-782 25 00

Telex
17978
PATOREG S

Telefax
+46 8 666 02 86
08-666 02 86

METHOD AND APPARATUS FOR MONITORING

Technical field

5 The present invention relates to a method and apparatus for monitoring the formation of a coating on a particle. Ultimately, the invention is focused on controlling the process of manufacturing a coating of a pharmaceutical product, such as a pellet, a tablet or a capsule.

Technical background

10 Generally, a coating of a pharmaceutical product consists of one or more films and each film consists of one or more layers. Below, "coating" is used as a comprehensive expression encompassing everything from an individual layer to a combination of several different films. Each film is the result of a single coating step, generally performed in a coating vessel, where for instance layers of the film are built up. The coating process takes
15 place either in a fluidized bed wherein particles, so-called nuclei, are sprayed with a specific coating liquid, or by passing the particles through a spray dust of said liquid. Several other generally used coating techniques are known in the prior art, such as melting, aggregation etc. The total process of manufacturing a complete coating may involve a plurality of such coating steps. However, the process may as well be sequential, whereby
20 the whole process represents a continuous flow.

Pharmaceutical products are coated for several reasons. A protective coating normally protects the active ingredients from possible negative influences from the environment, such as for example light and moisture but also temperature and vibrations.
25 By applying such a coating, the active substance is protected during storage and transport. A coating could also be applied to make the product easier to swallow, to provide it with a pleasant taste or for identification of the product. Further, coatings are applied which perform a pharmaceutical function such as conferring enteric and/or controlled release. The purpose of a functional coating is to provide a pharmaceutical preparation or formulation
30 with desired properties to enable the transport of the active pharmaceutical substance through the digestive system to the region where it is to be released and/or absorbed. A desired concentration profile over time of the active substance in the body may be obtained by such a controlled course of release. An enteric coating is used to protect the product from disintegration in the acid environment of the stomach. Moreover, it is important that
35 the desired functionalities are constant over time, i.e. during storage. By controlling the

quality of the coating, the desired functionalities of the final product may also be controlled.

5 There are strict requirements from the different Registration Authorities on pharmaceutical products. These requirements will put high demands on the quality of the coating and require that the complex properties of the coating will be kept within narrow limits. In order to meet these demands, there is a need for accurate control of the coating process.

10 The quality of the coating depends on physical and/or chemical properties of the coating, such as chemical composition, local inhomogeneities, physical and chemical homogeneity, density, mechanical properties, static parameters, modulus, tensile strength, elongation at break, compression, ductility, viscoelastic parameters, morphology, macro- and microscopic properties, amorphous and/or crystallinity, permeability, porosity, 15 aggregation, wettability, degree of coalescence/maturity, stability and ability to resist chemical and/or physical degradation. There are also other properties not listed above. The quality of the coating affects to a great extent the release properties and has a significant impact on the storage stability. In order to keep the quality of the coating within the desired narrow limits it is necessary to control the manufacturing process of the coating accurately.

20 In an industrial plant for coating pharmaceutical products, selected process parameters are monitored and controlled to achieve a desired quality of the end product. Such process parameters are generally global and could include, for example, the pressure in the coating vessel, the flow rate and temperature of gas and coating liquid supplied to 25 the coating vessel, etc. However, the influence of such global process parameters on the coating process, and ultimately on the coating properties of the end product, is known only from experience in a specific plant. Thus, a processing scheme is developed for each specific plant by extensive testing. When, for example, the size or shape of the coating vessel is changed during scaling up of the process, the local environment of the particles 30 may be altered. This calls for time-consuming measurements and adjustments in order to regain the same coating properties of the end product.

35 There is also a need to improve existing manufacturing processes as well as to improve existing plants. Today, this is a laborious task since the influence of any change in the process scheme or the plant design on the end product has to be investigated by

extensive testing, often in full scale. The same applies to the development of new products, for example when a new type of particle or coating liquid should be used.

An attempt to fulfil the above-identified needs is disclosed in the article "Fluidized bed spray granulation, investigation of the coating process on a single sphere" by K. C. Link and E.-U. Schlünder, published in Chemical Engineering and Processing, No. 36, 1997. A laboratory-scale apparatus is designed for analysis of a single particle, in order to investigate the fundamental physical mechanisms that lead to particle growth by layering. In this apparatus, a single aluminum sphere is made to levitate on a fluidizing air flow which is supplied by a capillary tube. Thereby, the sphere is freely and rotatably suspended at a stable location in a coating vessel. An ultrasonic nozzle arranged above this stable location is intermittently activated to generate a spray dust of coating liquid that falls down onto the sphere and forms a coating thereon. This type of nozzle generates a spray of droplets, the velocity of which is adjusted by means of a separate air flow through the nozzle. The apparatus is used for investigating the influence of different parameters, such as droplet velocity, temperature of fluidizing air, drying time, and type of coating liquid, on the thickness and morphology of the resulting coating. A rough measurement value of the overall thickness of the coating is obtained by weighing the sphere before and after the actual coating process and determining the difference in weight. The morphology of the coating is qualitatively examined by arranging the sphere, once coated, in a scanning-electron-microscope (SEM). For both of these measurements, the sphere must be removed from the apparatus for analysis. The apparatus also includes a lamp for illumination of the sphere and a video camera for continuous and qualitative observation of the contours of the sphere during the coating process.

25

One drawback of this prior-art apparatus resides in the difficulty to make quantitative, time-resolved measurements of coating properties. After a specific time period, the coating process must be interrupted for analysis of the coating on the sphere, whereupon a new and non-coated sphere must be subjected to a new coating process for a longer time period, and so on. In this approach, the formation of a coherent time series of measurement data requires that identical conditions are maintained in the environment of each sphere. Thus, the coating process must be repeated in exactly the same manner for each sphere. This is difficult. For example, any small variations in the masses of the aluminum spheres will necessitate an adjustment in the flow rate of the fluidizing air, to maintain each sphere at the same location in the vessel. Such a change in flow rate will also change the environment of the sphere during the coating process, thereby making it

30
35

difficult to compile the measurement data from several consecutive measurements into a coherent time series.

5 A further drawback of this known apparatus is that only a few properties of the coating, i.e. average thickness and surface morphology, can be measured.

Another drawback is that the course of a coating process can only be studied on standardized spheres, so that the coating process can be repeated in exactly the same manner for each sphere. However, the coating process is believed to be highly dependent
10 on the properties of the particle itself, such as the size, density, porosity and shape of the particle. Thus, it may be difficult, or even impossible, to draw any conclusions for a realistic particle from experiments made in the known apparatus.

Summary of the invention

15 The object of the invention is to solve or alleviate some or all of the problems described above. More specifically, the method and apparatus according to the invention should allow for time-resolved measurements of coating properties on any type of particle.

20 This object is achieved by the method and apparatus set forth in the appended claims.

The inventive method and apparatus will allow for continuous and non-invasive monitoring of one or more principal parameters related to the coating, such as thickness, thickness growth rate and physical and/or chemical properties related to the quality of the
25 coating, as well as heat, mass and momentum transfer, during the coating process on a single particle. The results of the measurements made possible by the inventive apparatus and method can be used to develop a fundamental model of the coating process on a single particle as a function of one or more control parameters, which can be related to properties of the environment of the particle and to properties of the particle itself. Ultimately, such a
30 fundamental model can be converted to an aggregate model for prediction of the influence of global process parameters on the monitored principal parameter or parameters for a large number of particles, for example in a full-scale coating process in an industrial plant. Such an aggregate model is a valuable tool that can be used to scale up processes and plants, improve existing manufacturing processes and plants, and develop new products.

35

It should also be noted that the invention allows for monitoring of the coating process on any type of single solid sample. Thus, in contrast to prior art technique, it is conceivable to use a realistic nucleus, such as a pellet, a tablet, or a capsule.

5 The inventive method and apparatus have the additional advantage of providing information that can be directly used in the control of a full-scale process. More specifically, by effecting a coating process on a single particle at well-controlled conditions, so that desired properties of the coating on the particle is obtained, and by continuously performing the spectrometric measurement, a desired sequence of
10 measurement values can be obtained. By effecting the same spectrometric measurement in a full-scale process, the global process parameters of this process can be controlled to yield the desired sequence of measurement values. Thereby, the full-scale process will be controlled to yield the desired properties of the coating on the particles. In practice, the sequence of measurement values could form a desired trajectory in a space that is defined
15 by one or more principal components. These principal components can be derived by applying chemometric methods to measurement data obtained from a time-series of spectrometric measurements. Evidently, the desired sequence of measurement values could also be established by effecting a spectrometric measurement on a batch of particles in the full-scale process itself. However, by means of the invention, the desired sequence of
20 measurement values is established much faster, since the coating process of a single particle is considerably shorter in time than the coating process of a batch of particles in a full-scale process.

In an alternative approach for direct control of a full-scale process, the inventive
25 method and apparatus are used to identify the interrelationship between control parameters, given by conventional sensors, and principal parameters, given by spectrometric methods. This is typically done by effecting a coating process on a single particle at well-controlled conditions, and by continuously performing a spectrometric measurement and simultaneously performing a measurement of one or more control parameters, such as a
30 fluidizing gas flow rate or a temperature. By identifying relevant control parameters in this way, the inventive method and apparatus could be used to establish a desired sequence of control parameter values. This sequence could then be directly transferred to a full-scale process, wherein the global process parameters of this process are controlled to form a corresponding desired sequence of global process parameter values. Thereby, the full-scale
35 process will be controlled to yield the desired properties of the coating on the particles.

Preferably, the step of forming the coating on the particle includes generating a single droplet of a coating fluid and making the droplet impinge on the particle. The use of a single droplet, or a sequence of such single droplets, instead of a spray dust, provides for a controlled deposition of coating fluid on the particle surface. Thus, the droplet size or the droplet generating rate can be controlled during a wetting period and be used as well-defined control parameters. The term "coating fluid" is used as a comprehensive expression encompassing everything from a pure coating liquid to a slurry or suspension of coating liquid and coating solids. Alternatively, the coating fluid could be a mixture of coating solids and a carrier gas. In this case, the term "coating droplet" would refer to a coating solid.

Preferably, the particle is fluidized on an upwardly directed gas flow, so that the particle is held at a given spatial location, while being freely rotatable at this location. Thus, the particle can be fixed so that a precise measurement can be effected, and rotating so that a uniform coating can be formed. The fluidizing gas flow has the additional function of drying the particle.

It is preferred that each droplet upon generation is moved into and allowed to follow the fluidizing gas flow to the particle. Thereby it is assured that each droplet impinges on the fluidized particle.

In another preferred embodiment, the control parameter is changed based, at least partly, on the measurement value. This type of feed-back control provides for in-line adjustments of the coating process on the single particle. Thereby it is possible to monitor the effects of a change in any control parameter during the coating process.

The control parameter could include a property of said gas flow, such as a flow rate, a temperature or a content of a solvent, for example water; a property of the particle, such as a size, a shape, a density or a porosity; a property of the droplets, such as a droplet size, a droplet generation rate or a concentration of a droplet constituent; a duration of a wetting period during the coating process; and a duration of a drying period during the coating process. In addition to the control parameters listed above, there are also other parameters not listed here.

Preferably, the spectrometric measurement is performed by means of near-infrared spectrometry and/or a spectrometric method based on Raman scattering and/or a

spectrometric method based on absorption in the UV, visible, or infra-red (IR) wavelength region, or luminescence, such as fluorescence emission, and/or imaging spectrometry.

Brief description of the drawings

In the following, a presently preferred embodiment of the invention, will be described in more detail, reference being made to the accompanying drawing which schematically shows a layout of a monitoring apparatus.

Description of a preferred embodiment

The monitoring apparatus disclosed on the drawing comprises a coating chamber 1, a gas supply unit 2, a coating liquid dispenser 3, a spectrometric measurement unit 4, and a main control unit 5. In the coating chamber 1, the coating process of a single particle P can be continuously and non-invasively monitored under well-controlled conditions.

A vertical tube 6 extends from a bottom portion 7 of the chamber 1 along a vertical center line of the chamber 1. The gas supply unit 2 is adapted to feed a gas in controlled amounts to the chamber 1. The unit 2 communicates with the tube 6 and a periphery portion 8 of the chamber 1. The flow of gas through the tube 6 is used to levitate or fluidize the particle at a given position in the chamber 1. The flow of shielding gas to the periphery portion 8 is used to minimize any gradients between the measurement unit 4 and the particle P, since such gradients might introduce errors in the spectrometric measurements. Although not shown on the drawing, it is realized that such shielding gas could be supplied to the periphery portion 8 at several locations around the perimeter of the chamber 1. Alternatively, or additionally, shielding gas could be fed through the bottom portion 7.

A control system is provided to accurately position the particle P. The control system includes a position sensor 9, for example an array detector, which is arranged at the periphery of the chamber 1 and is adapted to output a position signal indicating to the position of the particle P. The position signal is fed to the main control unit 5, which adjusts the gas flow rate accordingly by feeding a control signal to the gas supply unit 2. The control system is capable of maintaining the particle P at a given position in the chamber 1. This position might be changed over time in a controlled manner, or be spatially fixed in the chamber 1.

The gas supply unit 2 is also adapted to condition the gas, for example by changing the gas temperature or the gas content of a solvent, such as water, based on corresponding

control signals received from the main control unit 5. To this end, the gas supply unit 2 could include a conventional bubbler system (not shown), in which the gas is bubbled through a liquid source to add a small concentration of liquid vapor to the gas. Such, and other, high-precision systems for mixing gas and liquid vapor are available on the market.

One or more coating liquid dispensers 3 (only one shown on the drawing) is connected to the tube 6 and is adapted to sequentially generate droplets D of a coating liquid. The generated droplets D are injected into the gas flow in the tube 6 and will, by following the gas flow to the particle P, impinge on the particle P and form a coating thereon. The coating liquid dispenser 3 receives control signals, indicating for example the desired droplet generation rate and droplet size, from the main control unit 5.

In the illustrated example, the coating liquid dispenser 3 is a flow-through microdispenser of the type disclosed in the article "Design and development of a silicon microfabricated flow-through dispenser for on-line picolitre sample handling", Journal of Micromechanical Microengineering No. 9, pp 369-376, 1999, by T. Laurell, L. Wallman and J. Nilsson. This microdispenser, of which no details are given in the drawing, comprises two joined silicon structures forming a flow-through channel. A piezoceramic element is connected to one of the silicon structures. By activating the piezoceramic element, a pressure pulse is generated in the channel, thereby ejecting a droplet from an orifice in the opposite silicon structure. This microdispenser allows for sequential generation of droplets with a well-defined size and frequency.

The spectrometric measurement unit 4 is arranged at the periphery of the chamber 1 and is adapted to perform a spectrometric measurement, preferably by NIRS (Near Infrared Spectrometry), on the coating during the coating process. The resulting measurement data are represented in a sample vector. The spectrometric measurement unit 4 is also adapted to evaluate the measurement data in the sample vector and derive a measurement value related to the coating. This measurement value is fed to the main control unit 5 for storage.

NIRS provides both physical and chemical properties of the coating. This spectrometric method, like several other commonly used spectrometric methods, is non-invasive as well as non-destructive. A NIRS measurement is fast and therefore, it is employable for continuously measuring samples of all kinds. The possibilities obtained by NIRS measurements will be further discussed below.

Further, with a spectrometric measurement according to the invention, it is possible to extract information from several different depths of the coating, i.e. from the surface as well from deeper levels thereof. Additionally, it is possible to directly measure the thickness of the coating. The spectrometric measurement can be carried out in such a manner that the particle P, the coating thickness of which is to be measured, is positioned at a desired level with respect to the measurement unit 4. Thus, the mean coating thickness or a variation of the coating thickness can be measured. By employing imaging spectrometry, local inhomogeneities in the coating can be measured. Imaging spectrometry also allows for variations in the position of the particle P during the spectrometric measurement.

In the spectrometric measurement unit 4, the sample vector is evaluated in order to extract information directly related to the quality of the coating. In one embodiment, the evaluation is performed by subjecting the sample vector to a mathematical analysis, weighting the data, in conjunction to previous data, and condensing them to at least one measurement value. In the present embodiment chemometric methods are used. More particularly and at least in the case of continuous measurements during the coating process, a multivariate analysis, such as PCA (Principal Component Analysis), or PLS (Partial Least Squares) is performed on the sample vector.

In this way, it is possible to directly measure the quality of the coating, in terms of relevant physical and/or chemical properties. As a further example, the heat transfer to the coating can be monitored by way of extracting a measurement value related to the surface temperature of the coating. Further, the mass transfer to the coating can be monitored by way of extracting a measurement value related to the moisture content of the coating.

The main control unit 5, for example a personal computer, is adapted to continuously store control parameters potentially affecting the coating process on the particle P in the chamber 1. Some control parameters are mentioned above, for example the gas temperature, the gas humidity, the droplet generation rate, and the droplet size. The main control unit receives additional control parameter information from a temperature sensor 10a, a mass flow meter 11 and a gas analyzer 12 arranged to measure the temperature, the flow rate and the solvent concentration, respectively, of the gas entering chamber 1 through tube 6, as well as a temperature sensor 13 and a gas analyzer 14 arranged to measure the temperature and the solvent concentration, respectively, of the gas leaving chamber 1. Additionally, a temperature sensor 10b is arranged to measure the

temperature of the shielding gas entering the chamber 1. Other such conventional sensors could be provided. Further control parameters could include the duty cycle of the coating liquid dispenser 3, i.e. the time period with wetting and drying, respectively, of the particle P. Further control parameters could be related to the particle P itself, or the concentration of a constituent of the coating liquid.

It is appreciated that one or more control parameters could be changed during the coating process, for monitoring its influence on the properties of the coating, as measured by the unit 4.

Examples of possible modifications comprise for example the use of other spectrometric methods, such as those based on Raman scattering, or absorption in the UV and visible or infrared (IR) wavelength regions or luminescence such as fluorescence emission.

Another example of a modification substitutes a more simple analysis to the chemometric methods as follows. Generally, when using spectrometric methods, broad response spectra are obtained. However, instead of analysing all of the measurement values obtained over such a broad response spectrum by applying chemometric methods, merely one or a few values of the measurement values are analysed. For example, the measurement values at a few individual frequencies could be analysed. Also, when employing Raman spectrometry, which often results in values well separated by wavelength, this simplified analysis can be useful.

CLAIMS

1. A method of monitoring the formation of a coating on a single particle (P), comprising the steps of: arranging the particle (P) at a given spatial location; forming said coating on the particle (P); and obtaining a measurement value of at least one principal parameter related to said coating, characterized in that said measurement value is obtained by performing a spectrometric measurement on said coating during said step of forming said coating.

2. A method as set forth in claim 1, wherein said spectrometric measurement is performed continuously during at least part of the step of forming said coating, thereby generating a sequence of measurement values of said at least one principal parameter.

3. A method as set forth in claim 1 or 2, wherein said step of arranging the particle (P) at a given spatial location includes fluidizing said particle (P) on an upwardly directed gas flow.

4. A method as set forth in any one of claims 1-3, wherein said step of forming said coating on the particle (P) includes generating a single droplet (D) of a fluid, and bringing said droplet to impinge on said particle (P).

5. A method as set forth in claims 3 and 4, wherein said droplet (D) upon said generation is moved into and allowed to follow said upwardly directed gas flow to said particle (P).

6. A method as set forth in claim 4 or 5, wherein said single droplet (D) is repeatedly generated, thereby forming at least one stream of such droplets (D) that sequentially impinge on said particle (P).

7. A method as set forth in any one of the preceding claims, further comprising a step of monitoring at least one control parameter related to the environment of the particle (P) or the particle (P) itself, and a step of identifying a functional relationship between said at least one control parameter and said at least one principal parameter.

8. A method as set forth in claim 7, further comprising a step of generating, based on said functional relationship for said single particle (P), an aggregate model for

prediction of the influence of said at least one control parameter on said at least one principal parameter for a large number of such particles (P).

9. A method as set forth in claim 7 or 8, further comprising the step of changing
5 said at least one control parameter based, at least partly, on said measurement value.

10. A method as set forth in any one of claims 7-9 in combination with claim 3 or 5,
wherein said at least one control parameter includes a property of said gas flow, such as a
flow rate, a temperature or a content of a solvent.

10

11. A method as set forth in any one of claims 7-9, wherein said at least one control
parameter includes a property of the particle (P), such as a size, a shape, a density or a
porosity.

15

12. A method as set forth in any one of claims 7-9 in combination with any one of
claims 4-6, wherein said at least one control parameter includes a property of said droplet
(D), such as a droplet size, a droplet generation rate or a concentration of a droplet
constituent.

20

13. A method as set forth in any one of claims 7-9 in combination with any one of
claims 4-6, wherein said at least one control parameter includes a duration of a wetting
period during said step of forming said coating, said wetting period being effected by
controlling said droplet generation.

25

14. A method as set forth in any one of claims 7-9 in combination with any one of
claims 4-6, wherein said at least one control parameter includes a duration of a drying
period during said step of forming said coating.

30

15. A method as set forth in any one of the preceding claims, wherein said step of
obtaining said measurement value includes generating a sample vector of measurement
~~data from said spectrometric measurement, and condensing said measurement data into~~
said measurement value of said at least one principal parameter.

35

16. A method as set forth in any one of the preceding claims, wherein said
spectrometric measurement is performed by means of near-infrared spectrometry.

17. A method as set forth in any one of the preceding claims, wherein said spectrometric measurement is performed by means of a spectrometric method based on Raman scattering.

18. A method as set forth in any one of the preceding claims, wherein said spectrometric measurement is performed by means of a spectrometric method based on absorption in the UV, visible, or infrared (IR) wavelength region, or luminescence, such as fluorescence emission.

19. A method as set forth in any one of the preceding claims, wherein said spectrometric measurement is performed by means of imaging spectrometry.

20. A method as set forth in any one of the preceding claims, wherein said particle (P) is a pharmaceutical product, such as a pellet a tablet or a capsule.

21. Use of a method as set forth in any one of the preceding claims for identifying a functional relationship between said at least one principal parameter and properties of an environment of the particle (P) during the formation of said coating, and/or properties of the particle (P) itself.

22. Use of a method as set forth in claim 2 for control of a coating process of a batch of particles, wherein said sequence of measurement values is used as a sequence of reference values in said control, and wherein a corresponding spectroscopic measurement is effected on said batch of particles to provide a sequence of actual values for said control.

23. Use of a method as set forth in any one of claims 1-20 for control of a coating process of a batch of particles, wherein a functional relationship is identified between said at least one principal parameter and at least one simultaneously monitored control parameter, which is related to an environment of said single particle (P); wherein one or more of said at least one control parameters, based on said functional relationship, is selected to represent one or more of said at least one principal parameters; wherein a desired sequence of values of said one or more selected control parameters is determined for said single particle (P); and wherein said coating process of a batch of particles is controlled based on said desired sequence of selected control parameter values.

24. An apparatus for monitoring the formation of a coating on a single particle (P), comprising means (2, 5, 6, 9) for arranging said particle (P) at a given spatial location, and a fluid supply unit (3) adapted to apply a coating fluid to said particle (P) such that said coating is formed, characterized by a measurement unit (4) which is adapted to perform a spectrometric measurement on said coating during formation thereof, and to derive a measurement value of at least one principal parameter related to said coating.

25. An apparatus as set forth in claim 24, wherein said measurement unit (4) is adapted to continuously perform said spectrometric measurement, thereby generating a sequence of measurement values of said at least one principal parameter.

26. An apparatus as set forth in claim 24 or 25, wherein said particle arranging means (2, 5, 6, 9) comprises a flow unit (2) which is adapted to generate a fluidizing gas flow on which the particle (P) is fluidized.

27. An apparatus as set forth in claim 26, further comprising a housing (1) in which said coating is formed on said particle (P), wherein said flow unit (2) is adapted to provide a shielding gas inside the housing (1) intermediate the measurement unit (4) and the location of said particle (P), said shielding gas being essentially identical to the gas used for fluidizing said particle (P).

28. An apparatus as set forth in any one of claims 24-27, wherein said fluid supply unit (3) is operable to generate a single droplet (D) that is brought to impinge on said particle (P).

29. An apparatus as set forth in claim 26 and 28, wherein said fluid supply unit (3) is arranged to inject each droplet (D) into said fluidizing gas flow.

30. An apparatus as set forth in claim 28 or 29, wherein said fluid supply unit (3) is arranged to repeatedly generate said single droplet (D), thereby forming a stream of such droplets (D) that sequentially impinge on said particle (P).

31. An apparatus as set forth in any one of claims 24-30, further comprising a control unit (5) which is adapted to monitor at least one control parameter related to the environment of the particle (P) or the particle (P) itself.

32. An apparatus as set forth in claim 31, wherein the control unit (5) is adapted to receive said measurement value from said measurement unit (4) and to effect a change of said at least one control parameter based, at least partly, on said measurement value.

5 33. An apparatus as set forth in claim 32 in combination with claim 26 or 28, wherein said at least one control parameter includes a property of said fluidizing gas flow, such as a flow rate, a moisture content or a temperature, and wherein said control unit (5) is operable to effect said change by controlling said flow unit (2).

10 34. An apparatus as set forth in claim 32 in combination with any one of claims 28-30, wherein said at least one control parameter includes a property of said droplets, such as a droplet size, a droplet generation rate or a concentration of a droplet constituent, and wherein said control unit (5) is operable to effect said change by controlling said fluid supply unit (3).

15 35. An apparatus as set forth in claim 32 in combination with any one of claims 28-30, wherein said at least one control parameter includes a duration of a droplet generation period, and wherein said control unit (5) is operable to effect said change by controlling said fluid supply unit (3).

20 36. An apparatus as set forth in claim 32 in combination with any one of claims 28-30, wherein said at least one control parameter includes a duration of a drying period, and wherein said control unit is operable to effect said change by controlling said fluid supply unit (3).

25 37. An apparatus as set forth in any one of claims 24-36, wherein said measurement unit (4) is adapted to perform said spectrometric measurement by means of near-infrared spectrometry.

30 38. An apparatus as set forth in any one of claims 24-37, wherein said measurement unit (4) is adapted to perform said spectrometric measurement by means of a spectrometric method based on Raman scattering.

35 39. An apparatus as set forth in any one of claims 24-38, said measurement unit (4) is adapted to perform said spectrometric measurement by means of a spectrometric method

based on absorption in the UV, visible, or infrared (IR) wavelength region, or luminescence, such as fluorescence emission.


40. An apparatus as set forth in any one of claims 24-39, wherein said measurement
5 unit (4) is adapted to perform said spectrometric measurement by means of imaging spectrometry.

41. An apparatus as set forth in any one of claims 24-40, wherein said particle (P) is a pharmaceutical product, such as a pellet, a tablet or a capsule.

7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
219

ABSTRACT

In a method of monitoring the formation of a coating on a single particle (P), an apparatus is used which comprises means (2, 5, 6, 9) for arranging said particle (P) at a given spatial location, and a fluid supply unit (3) adapted to apply a coating fluid to the particle (P) such that the coating is formed. Further, the apparatus has a measurement unit (4) which is adapted to perform a spectrometric measurement on the coating during formation thereof, and to derive a measurement value of at least one principal parameter related to the coating. Thus, such principal parameters, for example thickness, thickness growth rate and physical and/or chemical properties related to the quality of the coating, as well as heat, mass and momentum transfer, can be continuously and non-invasively monitored during the coating process on the single particle (P). The results of such measurements can be used to understand the coating process on the single particle (P), and ultimately to control, up-scale and develop industrial full-scale coating plants.



1-08000000

